

## **RETARDER MC**

Retarder MC is used to extend the working time of Design-Casts 62 or 66. This is particularly useful when working in hot weather, because heat normally reduces the working time of either material.

Use up to 0.25% of retarder based on the weight of dry mix - typically this can double the working time for a given temperature. 0.25% amounts to about 25 drops of retarder per lb. of dry mix.

To mix in, add the retarder to the water/polymer mixture before adding the dry mix.

### DISCLAIMER and WARRANTY LIMITATIONS

The Manufacturer considers the information in this bulletin to be accurate. However, this information is to be taken as suggestions, not guarantees. Since the use of the materials is beyond the control of the Manufacturer, no warranty is expressed or implied regarding the results to be obtained by the Purchaser, or that such use will not infringe any patent.

The Manufacturer's or Seller's only obligation shall be to replace or pay for, at the Manufacturer's or Seller's discretion, material proven to be defective. Beyond the purchase price, neither Manufacturer nor Seller assumes any liability for damages of any kind, neither direct nor consequential, and the Purchaser accepts all risk and liability whatsoever in connection with any intended use for the material.

**DESIGN-CAST® is a registered trademark.**